



TECHNICAL DATA SHEET

Dosenasphalt-Emulsion

Product description

Cationic bitumen emulsion as a binder component for the production of asphalt mixtures.

Technical characteristics

Characteristic	Result	Unit	Test according to
Texture	brown liquid	–	ÖN EN 1425
Smell	slightly bitumen-like	–	ÖN EN 1425
Binder content	45-48	M %	ÖN EN 1428
Boiling point	100	°C	–
Viscosity [25 °C]	10 – 100	mPas	ÖN EN 13302
pH – value	2 – 3	–	ÖN EN 12850
Degree of stability	stable	–	ÖN EN 13075-1 / ÖN EN 1429

Instructions for Use

Store in a frost-proof place and homogenize the container every 6 weeks by shaking it to prevent the formation of a compact sediment which is hard to stir up.

Attention:

Our technical data sheet contains the results we have achieved in our previous application experience with the product we offer. The information in this data sheet is intended as general guidelines and must be individually adapted by the customer to the intended application and local conditions. Our customers must check for themselves whether our material is suitable for their intended purposes and conditions.