



TECHNICAL DATA SHEET

Rephalt 0/8

Product Description

Reactive hardening, cold processable asphalt mix, free of solvents according to RVS 08.97.01.

Technical Characteristics

Property	Result	Unit	Test according to (*)
Binder content	7 – 8	M%	ÖN EN 12697-1
VOC	0	M%	ÖN EN 14039
Biogenic raw material content	20 - 50	M%	ONR CEN/TS 16640
Stone material	–	–	ÖN EN 13043
Void content	< 8	Vol.-%	ÖN EN 12697-8
Grain loss at -20°C	< 30	M%	ÖN EN 12697-17
ITSR: Splitting tensile strength after water storage at 25°C	> 80	%	ÖN EN 12697-12
ITSw: Remaining splitting tensile strength after water storage at 25°C	0,2 – 0,5	N/mm ²	ÖN EN 12697-12
Marshall stability after 72 h at 60 ° C in the water bath	> 5	kN	ÖN EN 12697-34

(*) The test is carried out on the basis of the relevant standard, if applicable

Version 4.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A – 5280 Braunau / Inn
Josef – Reiter – Straße 78, Tel. 07722 / 62977 – 0, Fax 07722 / 65758
office@vialit.at www.vialit.com www.rephalt.com