



TECHNICAL DATA SHEET

RBT for Reactive-Patch

Product Description

Reactive binder component A for Reactive-Patch.

Technical characteristics

Property	Result	Unit	Test according to (*)
Viscosity [40 °C]	1000 – 1700	mPas	ÖN EN 13302
Moisture content	< 0,1	%	ÖN EN 12697 – 3
Flashpoint	≥ 150	°C	ÖN EN ISO 13736

Technical characteristics (hardened)

Property	Result	Unit	Test according to (*)
Softening point R&B	70 – 75	°C	ÖN EN 1427
Adhesion behavior	≥ 90	%	ÖN EN 15626

(*) The test is carried out on the basis of the relevant standard, if applicable

Version 1.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A – 5280 Braunau / Inn
Josef – Reiter – Straße 78, Tel. 07722 / 62977 – 0, Fax 07722 / 65758
office@vialit.at www.vialit.com www.rephalt.com