



TECHNICAL DATA SHEET

Refug 100

Product Description

Reactively curing, cold applied two component binder for joint filling (mixing ratio 100 : 10).

Technical characteristics (hardened)

Property	Result	Unit	Test according to (*)
Specific weight	$\geq 1,08$	g / cm ³	ÖN EN 15326
Softening point R & B	≥ 85	°C	ÖN EN 1427
Konus – penetration [25 °C]	22	1/10 mm	ÖN EN 13880 – 2
Stretching and adhesiveness [-15 °C; 5 mm]	0,47	N/mm ²	ÖN EN 13880 – 13
Falling ball test after Herman [-20 °C]	passed	fall height 4 m	DIN 1996 – 18

(*) The test is carried out on the basis of the relevant standard, if applicable

Version 4.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A – 5280 Braunau / Inn
Josef – Reiter – Straße 78, Tel. 07722 / 62977 – 0, Fax 07722 / 65758
office@vialit.at www.vialit.com www.rephalt.com