



TECHNICAL DATA SHEET

Refug 2K

Product Description

Reactively curing, cold and manually processable two component binder for joint filling (mixing ratio 100 : 8).

Technical characteristics (hardened)

Property	Result	Unit	Test according to (*)
Specific weight	≥ 1,05	g / cm ³	ÖN EN 15326
Softening point R & B	≥ 75	°C	ÖN EN 1427
Konus – penetration [25 °C]	40 – 60	1/10 mm	ÖN EN 13880 – 2
Ductility after Raabe [-20 °C]	≥ 5	mm	ÖN EN 13880 – 13
Falling ball test after Herman [-20 °C]	passed	fall height 5m	DIN 1996 – 18

(*) The test is carried out on the basis of the relevant standard, if applicable

Version 4.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A – 5280 Braunau / Inn
Josef – Reiter – Straße 78, Tel. 07722 / 62977 – 0, Fax 07722 / 65758
office@vialit.at www.vialit.com www.rephalt.com