



TECHNICAL DATA SHEET

Replast

Product Description

Reactively curing, cold-processable, bituminous two-component product for binder enrichment of hot asphalt finisher seams.

Technical characteristics (hardened – Mixing ratio A : B = 1 :1)

Property	Result	Unit	Test according to (*)
Ash content	10 – 20	%	DIN 52002
Softening point R & B	70 – 75	°C	ÖN EN 1427
Elastisches Rückstellverhalten	10 – 30	%	ÖN EN 13380-3
Ductility and adhesion [-10 °C]	≤ 1	N/mm ²	SNV 671920
Ductility and adhesion after heat reduction [-10 °C]	≤ 1	N/mm ²	SNV 671920
Cone penetration	20 – 50	1/10 mm	ÖN EN 13880-2

(*) The test is carried out on the basis of the relevant standard, if applicable

Version 4.0

Vialit Asphalt Gesellschaft m.b.H. & Co.KG, A – 5280 Braunau / Inn
Josef – Reiter – Straße 78, Tel. 07722 / 62977 – 0, Fax 07722 / 65758
office@vialit.at www.vialit.com www.rephalt.com